

## KWO® MultiTex® Tape – ePTFE gasket tape



The innovative product is ideally suitable for large and irregularly shaped steel flanges and glass-lined steel flanges.

The flexible material made of 100% multi-directional expanded PTFE is chemically inert, and highly resistant to creep, cold flow and clamp-force loss.

KWO® MultiTex® Tape maintains an extra tight seal even at low loads.



### ★ Advantages

- > adapts well to sealing surfaces
- > compensates irregularities
- > superior resistance to creep and cold flow
- > very high sealability especially at very low stresses
- > harmless in contact with food

### ⚙ Properties

- > high chemical resistance
- > UV resistant, non-ageing
- > nontoxic, biologically inert
- > non-flammable

### 🏠 Applications

- > heat exchangers, apparatus constructions
- > glass-lined flanges, reactors
- > GRP-pipelines and -tanks
- > pharmaceutical- and food processing equipment

### 🏆 Certificates

- > BAM - suitable for use with oxygen
- > TA Luft regulation and blow out safety acc. to VDI 2200
- > specific values according to DIN EN 13555
- > FDA 21 CFR 177.1550 compliant
- > EC1935/2004 - suitable for food applications

## TECHNICAL DATA

<b>Material</b>	100% multidirectional expanded PTFE (ePTFE) - self-adhesive
<b>Chemical resistance</b>	in the entire pH range (pH 0-14, except molten alkali metals and elemental fluorine)
<b>Temperature range</b>	-268°C (-450°F) up to +270°C (+518°F), short-term +315°C (+600°F) recommended temperature range: from -160°C (-256°F) to +230°C (+446°F)*
<b>Pressure range</b>	vacuum up to 200bar (3000psi) depending on the installation situation*
<b>Physiologically inert</b>	physiologically harmless in all recommended applications
<b>Density</b>	0,65 g/cm <sup>3</sup> +/-0,10g/cm <sup>3</sup>

\*Note: temperature and pressure guides cannot necessarily be used simultaneously.

## Quality assurance

The KWO Quality Management is certified according to DIN EN ISO 9001. Our suppliers are also integrated in this quality system. We use exclusively high quality raw materials in the fabrication of our products, which provide the highest level of safety and reliability.




Teflon™ is a trademark of The Chemours Company FC, LLC used under license by KWO Dichtungstechnik GmbH.

## Available Dimensions

Width* [mm]	Thickness* [mm]			
	2	3	6	9
10	X	X	X	
15	X	X	X	X
20	X	X	X	X
25	X	X	X	X
30	X	X	X	X
40	X	X	X	X
50		X	X	X
55		X	X	X
60		X	X	X

\*Other dimensions available on request.



To order, please use the following text


MultiTex Tape, \_\_ x \_\_ mm - \_\_ m, quantity in meter  
 (width) (thickness) (spool length)

The p-T diagram indicates the service limits considering the simultaneous influence of pressure and temperature.

- Range 1: Typical service limits
- Range 2: Maximum application limits, after technical verification

## Values

Q <sub>MIN</sub> (0,01)	28 MPa	DIN EN 13555
Q <sub>S MIN</sub> (0,01)	<<10 MPa	DIN EN 13555
PQR(at Q <sub>smax</sub> 20°C)	0,95	DIN EN 13555
PQR(at Q <sub>smax</sub> 150°C)	0,64	DIN EN 13555



- ✓ Made in Germany
- ✓ International Presence
- ✓ Represented in over 46 countries

For detailed selection criteria, technical information, installation guideline and the relevant contact person, please visit our website: [www.kwo-ptfe.de](http://www.kwo-ptfe.de)

## KWO Dichtungstechnik GmbH

Am Eschengrund 3  
 83135 Schechen, Germany  
 Tel: + 49 8039 90254-0  
 Fax: + 49 8039 90254-299  
 Email: [info@kwo-ptfe.de](mailto:info@kwo-ptfe.de)



All technical information and advice given here is based on our previous experiences and/or test results. We give this information to the best of our knowledge, but assume no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. Specifications are subject to change without notice. KWO's terms and conditions of sale apply to the purchase and sale of the product.