

Product information

PTFE sealing technologies

02/2018-EN

KWO® Universal F Premium - ePTFE joint sealant tape

MADE IN GERMANY

KWO® Universal F Premium is a joint sealant tape made from 100% pure, monoaxially expanded PTFE and especially suitable for food and pharmaceutical applications.

The exceptional malleability of the ePTFE joint sealant tape can compensate for out-of-parallel or damaged sealing surfaces and allows use with stress sensitive connections and applications where only a limited flange load is available.

KWO® Universal F Premium is the universal sealing solution on a roll, which can instantly be formed in place to fit any shape, regardless of flange size or complexity.



\star Advantages

- > adapts well to sealing surfaces
- > compensates irregularities
- > simple and fast installation
- > reduced down time, cost effective seal
- > harmless in contact with food

C Applications

- > flange connections, tank sealings
- > heat exchangers, apparatus constructions
- > flue gas plants
- > glass-lined flanges, reactors
- > machine housings, pumps
- > pharmaceutical- and food processing equipment

Certificates

Properties

>

>

>

> BAM - suitable for use with oxygen

excellent chemical resistance

UV resistant, non-ageing

nontoxic, biologically inert

- > TA Luft regulation and blow out safety acc. to VDI 2200
- > specific values according to DIN EN 13555
- > certified by DVGW
- > FDA 21 CFR 177.1550 compliant
- > EC 1935/2004 suitable for food applications
- > certificated and monitored by TÜV

TECHNICAL DATA

| Material | 100% expanded PTFE (ePTFE) - self-adhesive | | |
|-----------------------|--|--|--|
| Chemical resistance | in the entire pH range (pH 0-14, except molten alkali metals and elemental fluorine) | | |
| Temperature range | -268°C (-450°F) up to +270°C (+518°F), short-term +315°C (+600°F) recommended temperature range: from -160°C (-256°F) to +150°C (+302°F)* | | |
| Pressure range | vacuum up to 200bar (3000psi) depending on the installation situation* | | |
| Physiologically inert | physiologically harmless in all recommended applications | | |
| Density | 0,65 g/cm ³ +/-10% | | |

* Note: temperature and pressure guides cannot necessarily be used simultaneously.

KWO® Universal F Premium

Quality assurance

experts in ePTRE

The KWO Quality Management is certified according to DIN EN ISO 9001. Our suppliers are also integrated in this quality system. We use exclusively high quality raw materials in the fabrication of our products, which provide the highest level of safety and reliability.



Teflon™ is a trademark of The Chemours Company FC, LLC used under license by KWO Dichtungstechnik GmbH.

R


Available Dimension

| Width x Thickness* [mm] | Spool Length [m] | | | | |
|----------------------------|------------------|----|----|----|--|
| | 5 | 10 | 25 | 50 | |
| 3x1,5 | | | Х | Х | |
| 5x2 | | Х | Х | Х | |
| 7x2,5 | | Х | Х | Х | |
| 10x3 | | Х | Х | Х | |
| 12x4 | | Х | Х | Х | |
| 14x5 | Х | Х | Х | Х | |
| 17x6 | Х | Х | Х | | |
| 20x7 | Х | Х | Х | | |
| 25x5 | Х | Х | Х | | |
| 25x8 | Х | Х | | | |
| 28x5 | Х | Х | Х | | |
| 40x5 | Х | Х | | | |

To order, please use the following text

Universal F Premium, __x __ mm - __ m, quantity in meter (width) (thickness) (spool length)

^{*}Other dimensions available on request




Made in Germany

International Presence

Represented in over 46 countries

The p-T diagram indicates the service limits considering the simultaneous influence of pressure and temperature.

Range 1:Typical service limitsRange 2:Maximum application limits, after
technical verification



For detailed selection criteria, technical information, installation guideline and the relevant contact person, please visit our website: www.kwo-ptfe.de

KWO Dichtungstechnik GmbH

Am Eschengrund 3 83135 Schechen, Germany Tel: + 49 8039 90254-0 Fax: + 49 8039 90254-299 Email: info@kwo-ptfe.de



All technical information and advice given here is based on our previous experiences and/or test results. We give this information to the best of our knowledge, but assume no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. Specifications are subject to change without notice. KWO's terms and conditions of sale apply to the purchase and sale of the product.