Product information

# PTFE sealing technologies

11/2022 (Rev. 3)

# KWO® MultiTex® Tape – ePTFE gasket tape



The innovative product is ideally suitable for large and irregularly shaped steel flanges and glass-lined steel flanges.

The flexible material made of 100% multi-directional expanded PTFE is chemically inert, and highly resistant to creep, cold flow and clampforce loss.

KWO® MultiTex® Tape maintains an extra tight seal even at low loads.









## Advantages

- adapts well to sealing surfaces
- compensates irregularities
- superior resistance to creep and cold flow
- very high sealability especially at very low stresses
- harmless in contact with food



# Properties

- high chemical resistance
- UV resistant, non-ageing
- nontoxic, biologically inert
- non-flammable



## [] Applications

- heat exchangers, apparatus constructions
- glass-lined flanges, reactors
- GRP-pipelines and -tanks
- pharmaceutical- and food processing equipment



### Certificates

- BAM suitable for use with oxygen
- TA Luft regulation and blow out safety acc. to VDI 2200
- specific values according to DIN EN 13555
- FDA 21 CFR 177.1550 compliant
- EC1935/2004 suitable for food applications

### TECHNICAL DATA

| Material              | 100% multidirectional expanded PTFE (ePTFE) - self-adhesive   |  |  |
|-----------------------|---|--|--|
| Chemical resistance   | in the entire pH range (pH 0-14, except molten alkali metals and elemental fluorine)  |  |  |
| Temperature range     | -268°C (-450°F) up to +270°C (+518°F), short-term +315°C (+600°F) recommended temperature range: from -160°C (-256°F) to +230°C (+446°F)* |  |  |
| Pressure range        | vacuum up to 200bar (3000psi) depending on the installation situation*  |  |  |
| Physiologically inert | physiologically harmless in all recommended applications  |  |  |
| Density               | 0,75 g/cm³ +/- 0,15 g/cm³   |  |  |

\*Note: temperature and pressure guides cannot necessarily be used simultaneously.





# Quality assurance

The KWO® Quality Management is certified by TÜV Süd according to DIN EN ISO 9001. Our suppliers are also integrated in this quality system. We use exclusively high quality raw materials in the fabrication of our products, which provide the highest level of safety and reliability.




Teflon™ is a trademark of The Chemours Company FC, LLC used under license by KWO® Dichtungstechnik GmbH.

#### **Available Dimensions**

| Width* | Thickness* [mm] |   |   |   |  |
|--------|-----------------|---|---|---|--|
| [mm]   | 2               | 3 | 6 | 9 |  |
| 10     | X               | X | X |   |  |
| 15     | X               | X | X | X |  |
| 20     | X               | Χ | Χ | X |  |
| 25     | X               | X | X | X |  |
| 30     | X               | X | X | X |  |
| 40     | X               | X | X | X |  |
| 50     |                 | X | X | X |  |
| 55     |                 | X | X | X |  |
| 60     |                 | X | X | X |  |

<sup>\*</sup>Other dimensions available on request.



## To order, please use the following text

KWO® MultiTex® Tape, \_\_ x \_\_ mm - \_ \_ m, quantity in meter (width) (thickness) (spool length)

The p-T diagram indicates the service limits considering the simultaneous influence of pressure and temperature.


Range 1: Typical service limits

Maximum application limits, after Range 2:

technical verification

#### Values

| QMIN (0,01)                    | 28 MPa   | DIN EN 13555 |
|--------------------------------|----------|--------------|
| <b>Q</b> S MIN (0,01)          | <<10 MPa | DIN EN 13555 |
| PQR <sub>(at Qsmax 20°C)</sub> | 0,95     | DIN EN 13555 |
| PQR(at Qsmax 150°C)            | 0,64     | DIN EN 13555 |





- Made in Germany
- International Presence
- Represented in over 50 countries

For detailed selection criteria, technical information, installation guideline and the relevant contact person, please visit our website: www.kwo-ptfe.de

#### KWO® Dichtungstechnik GmbH

Am Eschengrund 3 83135 Schechen, Germany

Tel: +49 8039 90254-0 Fax: + 49 8039 90254-299

Email: info@kwo-ptfe.de



All technical information and advice given here is based on our previous experiences and/or test results. We give this information to the best of our knowledge, but assume no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available.