Product information

PTFE sealing technologies

02/2018-EN

KWO® CellFlon® Sheet White - sPTFE gasket sheet




KWO® CellFlon® Sheet White is a gasket sheet material containing structured PTFE and Barium Sulphate.

KWO® CellFlon® Sheet White is especially for use in the chemical and petrochemical industry.

Suitable for sealing most chemicals across the whole pH range (0-14), including strong acids, hydrocarbons, steam, solvents and others.









* Advantages

- universal purpose applications
- excellent sealability
- reduced cold flow
- easy to install and remove without residue



Properties

- high chemical resistance
- UV resistant, non-ageing, unlimited storable
- non-flammable



Applications

- flange connections
- closing lids
- reactors
- process vessels



Certificates

- TA Luft regulation and blow out safety acc. to VDI 2200
- FDA 21 CFR 177.1550 tested
- specific values according to DIN EN 13555

TECHNICAL DATA

Material	structured PTFE with Barium Sulphate		
Chemical resistance	in the entire pH range (pH 0-14, except molten alkali metals or elemental fluorine)		
Temperature range	recommended temperature range: from -210°C (-346°F) to +260°C (+500°F), material heat resistant up to +315°C (+600°F)*		
Pressure range	vacuum up to 80bar (1200psi) depending on the installation situation*		
Physiologically inert	physiologically harmless in all recommended applications		
Density	2,8 g/cm³		

^{*} Note: temperature and pressure guides cannot necessarily be used simultaneously.





Quality assurance



The KWO Quality Management is certified according to DIN EN ISO 9001. Our suppliers are also integrated in this quality system.


Available Dimension

Length x Width	Thickness [mm]*		
[mm]	1,5mm	2,0mm	3,0mm
1500 x 1500	Χ	X	Χ

^{*}Other dimensions available on request.

To order, please use the following text

CellFlon Sheet White, 1500x1500x _ _mm, Pieces (Length) (Width) (Thickness)




The p-T diagram indicates the service limits considering the simultaneous influence of pressure and temperature.

Range 1: Typical service limits

Range 2: Maximum application limits, after technical

verification





- Made in Germany
- International Presence
- Represented in over 46 countries

For detailed selection criteria, technical information, installation guideline and the relevant contact person, please visit our website: www.kwo-ptfe.de

KWO Dichtungstechnik GmbH

Am Eschengrund 3 83135 Schechen, Germany

Tel: +49 8039 90254-0

Fax: +49 8039 90254-299 Email: info@kwo-ptfe.de



All technical information and advice given here is based on our previous experiences and/or test results. We give this information to the best of our knowledge, but assume no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available.