

Product information

PTFE sealing technologies

11/2022 (Rev. 5)

MADE IN

KWO[®] MultiTex[®] Sheet HD – ePTFE gasket sheet

KWO[®] MultiTex[®] Sheet HD is produced from 100% multidirectional expanded PTFE with a high density and without any pigments or adhesives.

The flexible material adapts well to sealing surfaces, compensates irregularities and seals at very low stress. Suitable for use in metallic flanged, as well as stress sensitive connections.

In addition to the printed sheets, which are intended for industrial use and enable clear traceability, we are also offering embossed sheets without ink, which are particularly suitable for ultra-clean applications such as in the food and pharmaceutical sector.



\star Advantages

- > high diffusion sealing
- > adapts well to sealing surfaces
- > compensates irregularities
- > superior resistance to creep and cold flow
- > very high sealability especially at very low stresses

Properties

- > high chemical resistance
- > UV resistant, non-ageing, unlimited storable
- > nontoxic, biologically inert
- > non-flammable

C Applications

- > flange connections, tank sealings
- > heat exchangers, apparatus constructions
- glass-lined flanges, reactors
- > pumps

🚼 Certificates

- > BAM suitable for use with fluid and gaseous oxygen
- > TA Luft regulation and blow out safety acc. to VDI 2200
- > specific values according to DIN EN 13555
- > FDA 21 CFR 177.1550 tested*
- > EC1935/2004 suitable for applications with food contact*
- > USP Plastic Class for pharmaceutical applications*
- * These certificates do not apply to printed MultiTex® HD sheets.

TECHNICAL DATA

Material	100% multidirectional expanded PTFE (ePTFE)		
Chemical resistance	in the entire pH range (pH 0-14, except molten alkali metals and elemental fluorine)		
Temperature range	-268°C (-450°F) up to +270°C (+518°F), short-term +315°C (+600°F) recommended temperature range: from -160°C (-256°F) to +230°C (+446°F)*		
Pressure range	vacuum up to 200bar (3000psi) depending on the installation situation*		
Physiologically inert	physiologically harmless in all recommended applications		
Density	1,05 g/cm ³ +/- 0,15 g/cm ³		

*Note: temperature and pressure guides cannot necessarily be used simultaneously.

KWO[®] MultiTex[®] Sheet HD

Quality assurance

experts in ePTRE

The KWO® Quality Management is certified by TÜV Süd according to DIN EN ISO 9001. Our suppliers are also integrated in this quality system. We use exclusively high quality raw materials in the fabrication of our products, which provide the highest level of safety and reliability.



Teflon™ is a trademark of The Chemours Company FC, LLC used under license by KWO® Dichtungstechnik GmbH.

Available Dimensions

Length x Width [mm]	Thickness [mm]*			
1524 x 1524	1,0	1,5	2	3

R

*Other dimensions available on request

300 [bar] 200 Druck / Pressure p 0 150 0 100 0 25 16 Range 1: Range 2: (2) 1 10 6 0 0 50 100 150 200 250 300

To order please use the following text:

KWO[®] MultiTex[®] HD Sheet, 1524x1524x _ _ mm, pieces (Length) (Width) (Thickness)


The p-T diagram indicates the service limits considering the simultaneous influence of pressure and temperature.

> Typical service limits Maximum application limits, after technical verification

Values

Q _{MIN (0,01)}	28 MPa	DIN EN 13555
Q S MIN (0,01)	<<10 MPa	DIN EN 13555
PQR(30 MPa 20°C)	0,94	DIN EN 13555
PQR(30 MPa 150°C)	0,67	DIN EN 13555
maintenance factor m	2,5	ASTM
seating stress y	2800 psi	ASTM

Temperature T [°C]



Made in Germany For detailed selection criteria, technical information, installation guideline and the relevant contact person, please visit our website: www.kwo-ptfe.de International Presence KWO® Dichtungstechnik GmbH Represented in over 50 countries Am Eschengrund 3 83135 Schechen, Germany Tel: + 49 8039 90254-0 Fax: + 49 8039 90254-299 Email: info@kwo-ptfe.de

All technical information and advice given here is based on our previous experiences and/or test results. We give this information to the best of our knowledge, but assume no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. without notice KWO's te and cor ns of sale app to the purchase and sale of the produc

KWO[®] Dichtungstechnik GmbH